



Cast Machinability Ratings

Machinability

		Cast Machinability Ratings		
UNS No.	Product Description	Machinability	UNS No.	Product Description
C83800	Leaded Semi-Red Brass	90	C90300	Tin Bronze
C84400	Leaded Semi-Red Brass	90	C90500	Tin Bronze
C84800	Leaded Semi-Red Brass	90	C92500	Nickel Phosphor Bronze
C89520	Bismuth Tin Bronze	85	C86500	Manganese Bronze
C89831	Bismuth Tin Bronze	85	C90700	Tin Bronze
C83600	Leaded Red Brass	84	C90800	Tin Bronze
C89833	Bismuth Tin Bronze	81	C90810	High Tin Bronze
C84200	Leaded Semi-Red Brass	80	C91000	Tin Bronze
C85700	Leaded Naval Brass	80	C91600	High Tin Bronze
C89320	Bismuth Tin Bronze	80	C91700	High Tin Bronze
C89325	Bismuth Tin Bronze	80	C94700	Nickel Tin Bronze
C93600	High-Leaded Tin Bronze	80	C95200	Aluminum Bronze
C93700	High-Leaded Tin Bronze	80	C95800	Nickel Aluminum Bronze
C93800	High-Leaded Tin Bronze	80	C96400	Copper Nickel
C93900	High-Leaded Tin Bronze	80	C91100	High Tin Bronze
C94000	High-Leaded Tin Bronze	80	C91300	Tin Bronze
C94100	High-Leaded Tin Bronze	80	C95900	Aluminum Bronze
C94300	High-Leaded Tin Bronze	80	C86300	Manganese Bronze
C89835	Bismuth Tin Bronze	70		
C89844	Bismuth Tin Bronze	70		
C92800	Leaded Tin Bronze	70		
C93200	Leaded Tin Bronze	70		
C93400	High-Leaded Tin Bronze	70		
C93500	High-Leaded Tin Bronze	70		
C97300	Nickel Silver Bronze	70		
C97600	Nickel Silver Bronze	70		
C86400	Manganese Bronze	65		
C95400	Aluminum Bronze	60		
C95410	Aluminum Bronze	60		
C95600	Nickel Aluminum Bronze	60		
C97800	Nickel Silver Bronze	60		
C86700	Manganese Bronze	55		
C95300	Aluminum Bronze	55		
C94800	Leaded Nickel Tin Bronze	50		
C95500	Nickel Aluminum Bronze	50		
C95510	Nickel Aluminum Bronze	50		
C99500	Special Alloy	50		
C92700	Leaded Tin Bronze	45		
C95520	Nickel Aluminum Bronze	45		
000000		40	1	

C92200

C92300

C92900

C86200

Leaded Tin Bronze

Leaded Tin Bronze

Leaded Nickel Tin Bronze

Manganese Bronze